

# LORD® Signlok 406 Adhesive

## Description

LORD® Signlok 406 adhesive is a two-component adhesive system designed for bonding a wide variety of prepared or unprepared metals and engineered plastics. LORD Signlok 406 adhesive can be used to replace welding, brazing, riveting and other mechanical fastening methods. This adhesive system is formulated to provide some of the highest impact and peel strengths available in a room temperature curing adhesive.

## Features and Benefits

**Versatile** – bonds a wide range of unprepared metals with minimal substrate preparation, as well as engineered thermoplastics including XENOY®, polycarbonate, ABS and acrylics.

**Temperature Resistant** – performs at temperatures from -40°F to +300°F (-40°C to +149°C).

**Environmentally Resistant** – resists dilute acids, alkalis, solvents, greases, oils, moisture, salt spray and weathering; provides excellent resistance to UV exposure.

**Non-Sag** – remains in position when applied on vertical or overhead surfaces, allowing for greater process flexibility.

**Precise Bondline** – allows precise control of the adhesive bondline thickness due to its content of glass beads.

## Application

**Surface Preparation** – Remove grease, loose contamination or poorly adhering oxides from metal surfaces. Normal amounts of mill oils and drawing compounds usually do not present a problem in adhesion. Most plastics require a simple cleaning before bonding. Some may require abrading for optimum performance.

**Mixing** – Mix adhesive with accelerator at a ratio of 2:1, adhesive to accelerator, by volume. Handheld cartridges will automatically dispense the correct volumetric ratio of each component. Even color distribution visually indicates a thorough mix. Once mixed, the adhesive cures rapidly.

*XENOY is a trademark of General Electric Company.*

## Typical Properties\*

	Adhesive (Part A)	Accelerator (Part B)
Appearance	Tan Paste	Off-white Paste
Density		
lb/gal	9.25-9.55	12.15-12.7
(kg/m <sup>3</sup> )	(1108-1144)	(1456-1522)
Flash Point, °F (°C)	59 (15)	≥200 (93)

\*Data is typical and not to be used for specification purposes.

# LORD TECHNICAL DATA

**Applying** – Apply mixed adhesive to bond surfaces using handheld cartridge or automatic meter/mix/dispense equipment. Contact your LORD representative if assistance is needed using this equipment.

**Curing** – Cure begins immediately once adhesive and accelerator are mixed. Complete cure requires 24 hours at room temperature. Mating surfaces must be held in contact during the entire curing process. Cure rate can be accelerated by applying modest heat [ $<150^{\circ}\text{F}$  ( $<66^{\circ}\text{C}$ )]. Cured adhesive is colored to visually indicate a full cure; cure color depends on the accelerator used.

**Cleanup** – Clean equipment and tools prior to the adhesive cure with solvents such as isopropyl alcohol, acetone or methyl ethyl ketone (MEK). Once adhesive is cured, heat the adhesive to  $400^{\circ}\text{F}$  ( $204^{\circ}\text{C}$ ) or above to soften the adhesive. This allows the parts to be separated and the adhesive to be more easily removed.

## Typical Cured Properties\*

Lap Shear Strength, psi (MPa)	
Aluminum	2000 (13.79)
Steel	2300 (15.86)
Peel Strength, pli (N/mm)	20-23 (3.5-4.0)
Aluminum	

\*Data is typical and not to be used for specification purposes.

## Typical Properties\* of Adhesive Mixed with Accelerator

Mix Ratio by Volume, Adhesive to Accelerator	2:1
Solids Content, %	100
Working Time, min @ $75^{\circ}\text{F}$ ( $24^{\circ}\text{C}$ )	8-11
Time to Handling Strength, min @ $75^{\circ}\text{F}$ ( $24^{\circ}\text{C}$ ) 50 psi Shear	12-17
Full Cure Time, hr @ $75^{\circ}\text{F}$ ( $24^{\circ}\text{C}$ )	24
Mixed Appearance	Tan Paste
Cured Appearance	Tan to Green

\*Data is typical and not to be used for specification purposes.

## **Shelf Life/Storage**

Shelf life of each component is 18 months when stored in a well ventilated area below 80°F (27°C) in original, unopened container. Storage temperatures of 40-50°F (4-10°C) are recommended. If stored cold, allow product to return to room temperature before using. Protect from exposure to ultraviolet light.

LORD Signlok 406 adhesive is flammable. Do not store or use near heat, sparks or open flame.

## **Cautionary Information**

Before using this or any LORD product, refer to the Safety Data Sheet (SDS) and label for safe use and handling instructions.

*For industrial/commercial use only.* Must be applied by trained personnel only. Not to be used in household applications. Not for consumer use.

# LORD TECHNICAL DATA

Values stated in this technical data sheet represent typical values as not all tests are run on each lot of material produced. For formalized product specifications for specific product end uses, contact the Customer Support Center.

Information provided herein is based upon tests believed to be reliable. In as much as LORD Corporation has no control over the manner in which others may use this information, it does not guarantee the results to be obtained. In addition, LORD Corporation does not guarantee the performance of the product or the results obtained from the use of the product or this information where the product has been repackaged by any third party, including but not limited to any product end-user. Nor does the company make any express or implied warranty of merchantability or fitness for a particular purpose concerning the effects or results of such use.

LORD and "Ask Us How" are trademarks of LORD Corporation or one of its subsidiaries.

---

LORD provides valuable expertise in adhesives and coatings, vibration and motion control, and magnetically responsive technologies. Our people work in collaboration with our customers to help them increase the value of their products. Innovative and responsive in an ever-changing marketplace, we are focused on providing solutions for our customers worldwide ... Ask Us How.

**LORD Corporation**  
**World Headquarters**

111 Lord Drive  
Cary, NC 27511-7923  
USA

**Customer Support Center** (in United States & Canada)

+1 877 ASK LORD (275 5673)

[www.lord.com](http://www.lord.com)

For a listing of our worldwide locations, visit [LORD.com](http://LORD.com).